



Europäisches Patentamt
European Patent Office
Office européen des brevets



Publication number: **0 378 404 B1**

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification: **31.08.94** (51) Int. Cl.⁵: **A61M 31/00, A61K 9/22**

(21) Application number: **90300301.0**

(22) Date of filing: **10.01.90**

(54) **Dispensing devices powered by hydrogel.**

(30) Priority: **12.01.89 US 296464**

(43) Date of publication of application:
18.07.90 Bulletin 90/29

(45) Publication of the grant of the patent:
31.08.94 Bulletin 94/35

(84) Designated Contracting States:
AT BE CH DE DK ES FR GB GR IT LI LU NL SE

(56) References cited:
EP-A- 0 052 917
US-A- 4 235 236
US-A- 4 320 759
US-A- 4 578 075
US-A- 4 615 698

(73) Proprietor: **PFIZER INC.**
235 East 42nd Street
New York, N.Y. 10017 (US)

(72) Inventor: **Curatolo, William John**
18 Patrick Place
Niantic Connecticut (US)

(74) Representative: **Lawrence, Malcolm Graham**
et al
Hepworth, Lawrence & Bryer
2nd Floor, Gate House South
Westgate Road
Harlow Essex CM20 1JN (GB)

EP 0 378 404 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

Description

This invention relates to devices useful for the controlled delivery of one or more beneficial agents to an environment of use. More specifically, this invention concerns such devices which are powered by hydrogel.

5 This invention also relates to the controlled delivery of one or more beneficial agents to an aqueous environment of use through the use of such hydrogel powered dispensing devices. Further, still, this invention is concerned with devices for the controlled delivery of one or more beneficial agents to the physiological fluid of animals including mammals such as human beings.

10 The desirability of controlled release of beneficial agents into an environment of use such as the physiological fluid of animals including mammals such as human beings is well known to those skilled in the relevant art. Controlled delivery of beneficial agents such as drugs can, for example, result in a relatively constant concentration of such agents in the physiological fluids of an animal instead of the more dramatic rises and subsequent decreases in concentration of such agents usually associated with periodic dosing. Furthermore, controlled delivery of drugs can eliminate certain deleterious effects sometimes associated

15 with a sudden, substantial rise in the concentration of certain drugs.

A variety of devices for the controlled delivery of beneficial agents have been described. Certain of those devices employ the physical phenomenon of diffusion for their operation. Examples of such diffusion driven devices are disclosed in US Patent 4,217,898. Other devices have been described which operate with the principle of colloidal osmotic pressure. Examples of such osmotically driven devices are discussed

20 in US Patents 3,845,770; 3,995,631; 4,111,202; 4,160,020; 4,439,196 and 4,615,698. Devices which employ a swellable hydrophillic polymer which polymer exerts pressure on a container and thereby forces drug therefrom is disclosed in US Patent 4,180,073. US Patent 4,327,725 (corresponding to EP-A-0,052,917) discloses a device which employs a layer of fluid swellable hydrogel to force beneficial agent out of the device through a specified and defined passageway. Other hydrogel powered devices containing such a

25 passageway for delivery of beneficial agents are disclosed in GB 2,140,687A.

In addition, US Patents 4,285,236 and 4,320,759 disclose systems for delivering a beneficial agent which are diffusion driven.

Applicant's co-pending European Patent Application No. 90300300.2 filed concurrently herewith and entitled "Dispensing Devices Powered by Lyotropic Liquid Crystals" discloses dispensing devices, powered

30 by lyotropic liquid crystals, for the controlled delivery of one or more beneficial agents to an environment of use.

It is an object of this invention to provide devices for the controlled delivery of one or more beneficial agents to an environment of use. Another object of this invention is to provide devices powered by hydrogel which will effect the controlled delivery of one or more beneficial agents to an aqueous environment of use.

35 Yet another object of this invention is to provide devices powered by hydrogel for the controlled delivery of one or more beneficial agents to the physiological fluids of an animal including a human being. This invention also has as an object the provision of a device to controllably deliver one or more beneficial agents which are insoluble or substantially insoluble in water or physiological fluids. Another object still of this invention is to provide devices powered by hydrogel which do not require a specified and defined

40 passageway to operate but, instead, comprise a plurality of pores. It is another object of this invention to provide devices powered by hydrogel which do not require a semi-permeable coating, but, instead, can employ a coating which is permeable to the beneficial agent. Further still, it is an object of this invention to provide devices powered by hydrogel which can assume a variety of shapes and sizes and devices which can be delivered to an environment of use in a capsule.

45 It is also an object of this invention to provide methods for the controlled delivery of one or more beneficial agents to an environment of use by administering to or otherwise placing the device of this invention into the environment.

These and other objects of this invention will be readily apparent to those skilled in the relevant art enabled by the disclosure herein.

50 This invention concerns devices for the controlled delivery of one or more beneficial agents to an environment of use which devices comprise a mixture of one or more beneficial agents and from 50 to 98 weight percent of hydrogel as defined below based on the total weight of the mixture surrounded by a coating of a material that is permeable to water and/or aqueous medium such as physiological fluid and which coating contains one or more holes and/or a plurality of pores. The pores in the coating can be

55 formed by mechanical/physical means or result from dissolution of a porosigen in the coating upon placing the devices in an aqueous environment of use.

This invention also concerns devices for the controlled delivery of one or more beneficial agents to an aqueous environment of use which devices comprise two adjacent layers, the first layer comprising a

mixture of one or more beneficial agents and hydrogel and the second layer comprising hydrogel of the same or different composition as the hydrogel in the first layer. Such devices have a coating comprising a material which is permeable to water and/or aqueous medium and which contains one or more holes and/or a plurality of pores such as the devices described above.

5 All of the devices of this invention optionally can include therein one or more excipients and/or osmotically effective solutes.

This invention also relates to capsules which contain one or more of the devices as described above.

Further, this invention concerns methods for the controlled delivery of one or more beneficial agents to an aqueous environment of use which comprise administering to or otherwise placing the devices and/or the capsules of this invention in the environment of use.

10 Figure 1 is a perspective view of one embodiment of the device (1) of this invention in the shape of a tablet.

Figure 2 is a cross-sectional view taken along line 2-2 of the device (1) shown in Figure 1.

Figure 3 is a cross-sectional view of another embodiment of the device (1) which is taken along line 2-2 of the device (1) shown in Figure 1 which device comprises two layers (6 and 7) within the surrounding coating (3) of the device (1).

Figure 4 is a cross-sectional view through the axis of another embodiment of the device (1) of this invention wherein the device (1) is a sphere or is substantially spherical in shape.

Figure 5 is a cross-sectional view through the axis of another embodiment of the device (1) of this invention wherein the device (1) is a sphere or is substantially spherical in shape and which comprises two-layers (6 and 7) within the surrounding coating (3) of the device (1).

Figure 6 is a cross-sectional view of another embodiment of the device (1) which is taken along line 2-2 of the device (1) shown in Figure 1 which comprises two layers (6 and 7) within the surrounding coating (3) of the device (1).

25 Figures 1-6 depict certain embodiments of the devices of this invention and are meant to be illustrative of such embodiments of the invention herein. The Figures are not to be construed as limiting in any way the scope of this invention to the embodiments depicted therein. Further, the various components of the devices depicted in the Figures are representational and are not necessarily drawn to scale.

Figure 1 shows one embodiment of the device (1) of this invention in the form of a tablet containing a plurality of pores (2).

Figure 2 is a cross-sectional view taken along line 2-2 of Figure 1 and shows the coating (3) of the device (1) which contains a plurality of pores (2) in and through the coating (3). A mixture (6) of one or more beneficial agents represented by dots (4) and hydrogel represented by wavy lines (5) is contained within the surrounding coating (3).

Figure 3 is a cross-sectional view of another embodiment of the device (1) shown in Figure 1 wherein the device (1) comprises two layers (6 and 7) within the surrounding coating (3). Figure 3 is a cross-sectional view taken along line 2-2 of Figure 1 and shows the coating (3) of the device (1) which contains a plurality of pores (2) in and through the coating (3). Contained within the surrounding coating (3) are a first layer (6) which comprises a mixture of one or more beneficial agents represented by dots (4) and hydrogel represented by wavy lines (5) and a second layer (7) which comprises hydrogel represented by wavy lines (8) which can be the same or different than hydrogel (5). Layer (7) is adjacent to layer (6) and comprises an area in contact therewith.

Figure 4 is a cross-sectional view through the axis of another embodiment of the device (1) of this invention wherein the device is a sphere or is substantially spherical in shape. The device (1) contains a plurality of pores (2) in and through the coating (3). Within the surrounding coating (3) is a mixture (6) of one or more beneficial agents represented by dots (4) and hydrogel represented by wavy lines (5).

Figure 5 is a cross-sectional view through the axis of another embodiment of the device (1) of this invention wherein the device (1) is a sphere or is substantially spherical in shape. The device (1) contains a plurality of pores (2) in and through the coating (3). Within the surrounding coating (3) are two layers (6 and 7). The outermost layer (6) comprises a mixture of one or more beneficial agents represented by dots (4) and hydrogel represented by wavy lines (5) and the innermost layer (7) comprises hydrogel represented by wavy lines (8) which can be the same or different than hydrogel (5).

Figure 6 is a cross-sectional view of another embodiment of the device (1) shown in Figure 1 which view is taken along line 2-2 of Figure 1 and which device (1) comprises two layers (6 and 7) within the surrounding coating (3). The coating (3) contains a plurality of pores (2) in and through the coating (3). Contained within the surrounding coating (3) are an outermost layer (6) which comprises a mixture of one or more beneficial agents represented by dots (4) and hydrogel represented by wavy lines (5) and an innermost layer (7) which comprises hydrogel represented by wavy lines (8) which can be the same or

different than hydrogel (5).

This invention relates to devices powered by hydrogel for the controlled delivery of one or more beneficial agents to an environment of use.

The hydrogels employed in the various embodiments of the devices of this invention are well known to those skilled in the relevant art. For example, U.S. Patent 4,327,725 describes various hydrogels. The term hydrogel, as used herein, shall be construed to mean a water swellable polymer or a combination of two or more such polymers. Such hydrogels, for the purpose of this invention, comprise polymeric materials which, when in contact with water or other aqueous medium, will absorb such water/medium and swell to a certain extent. Such absorption can be reversible or irreversible and still be within the scope of this invention. A preferred hydrogel for use in the devices of this invention is polyethylene oxide (PEO). PEO is commercially available and can be obtained having a variety of different molecular weights. For example, PEO can be obtained with molecular weights of 8K, 14K, 100K, 400K, 600K, 1,000K or 5,000K. The particular molecular weight of PEO or other hydrogels employed in the devices of this invention will vary as a function of the pore size in the coating and the release rate which is to be achieved for the particular beneficial agent or agents to be delivered.

In the two layer embodiments of the devices of this invention, such as those shown in Figures 3, 5 and 6, the hydrogel of each layer may be the same or may be different. In the embodiment depicted in Figure 3, it is preferred that the hydrogel (8) of layer (7) be of a higher molecular weight than hydrogel (5) of layer (6). Still more preferably, the hydrogel (8) of such an embodiment as shown in Figure 3 should be of a sufficiently high molecular weight that substantially no hydrogel is capable of leaving the device (1) through the pores (2). However, since certain hydrogels such as PEO increase in viscosity as a function of increase in molecular weight, the hydrogel (5) and (8) must be chosen or blended such that it provides sufficient swelling properties but does not cause the device to burst. Selection of the appropriate hydrogel (5) and (8) for such devices is within the skill of those who practice in the relevant art enabled by the disclosure herein.

The hydrogel employed in the various embodiments of the devices of this invention can be a blend of, for example, two or more polymers. By way of example and not of limitation, different hydrogels comprising blends of PEO polymers of different molecular weights can be prepared and employed in the devices of this invention and are deemed within the scope hereof. Such blends can, for particular beneficial agents, be adjusted to assist in achieving the desired delivery rates for the agents.

In addition to the hydrogel(s), the devices of this invention may also contain an osmotically effective solute for the purpose of providing a colloidal osmotic pressure which is additive with the swelling pressure of the hydrogel(s). Examples of osmotically effective solutes are inorganic and organic salts, and sugars. A preferred composition comprising such a solute contains a range of 0-30% osmotically effective solute. Of course, for the devices of this invention which are to be employed to deliver a drug to an animal, any such solute must be pharmaceutically acceptable.

The devices of this invention comprise, in addition to the hydrogel and the optional osmotically effective solute described above, one or more beneficial agents. The term beneficial agents as used in this specification and the accompanying claims includes, by way of example and not of limitation, any physiologically or pharmacologically active substance that produces a localized or systemic effect in animals. The term animals is meant to include mammals including human beings as well as other animals. The physiologically or pharmacologically active substance of this invention need not be soluble in water. Indeed, an advantage of the devices of this invention is that such insoluble or partially insoluble substances as well as soluble substances can be delivered to the environment of use in a controlled fashion by the devices hereof.

Examples of active substances employed in the devices of this invention include, without limitation, inorganic and organic compounds such as drugs that act on the peripheral nerves, adrenergic receptors, cholinergic receptors, nervous system, skeletal muscles, cardiovascular smooth muscles, blood circulatory system, synaptic sites, neuroeffector junctional sites, endocrine and hormone systems, immunological system, reproductive system, autocoid systems, alimentary and excretory systems, inhibitors of autocoids and histamine systems. The drug that can be delivered for acting on these systems includes antidepressants, hypnotics, sedatives, psychic energizers, tranquilizers, anti-convulsants, muscle relaxants, antiseptics, anti-parkinson agents, analgesics, anti-inflammatory agents, local anesthetics, muscle contractants, antibiotics, anti-microbials, anthelmintics, anti-malarials, hormonal agents, contraceptives, histamines, antihistamines, adrenergic agents, diuretics, antiscabiosis, anti-pediculars, anti-parasitics, anti-neoplastic agents, hypoglycemics, electrolytes, vitamins, diagnostic agents and cardiovascular drugs.

Also included in such active substances are prodrugs of the above-described drugs. Such drugs or prodrugs can be in a variety of forms such as the pharmaceutically acceptable salts thereof. However, a particular advantage of the devices of this invention is that such beneficial agents, such as the drugs and

prodrugs described above, need not be soluble in water in order for the devices of this invention to deliver, in a controlled manner, such agents. It is within the scope of this invention that the devices can contain more than one beneficial agent.

Devices of this invention are particularly advantageous for delivering two or more drugs simultaneously.

5 The rate of drug release is controlled primarily by the extrusion rate of hydrogel and is relatively independent of the solubility of the incorporated drugs. Thus two or more incorporated drugs will be released at absolute rates which depend upon their individual loadings in the device. For example, devices of the current invention can be used to co-deliver a sustained dose of an α -blocker, such as prazosin, and a diuretic, such as polythiazide, for the treatment of hypertension. For the treatment of cold symptoms,

10 devices of this invention can be used to deliver a combination of a decongestant, such as pseudoephedrine hydrochloride, and an antihistamine, such as chlorpheniramine maleate. For treatment of cough/cold symptoms, three or more drugs can be released in a controlled fashion from a device of this invention; for example a combination of an analgesic, a decongestant, an antihistamine, and an antitussive can be delivered. A person skilled in the art will recognize that the current invention can be used to provide

15 controlled and sustained delivery of a wide variety of combinations of drugs.

The beneficial agent of this invention also includes other substances for which it is desirable and/or advantageous to control delivery into an environment of use. Examples of such substances include, but are not limited to, fertilizers, algicides, reaction catalysts and enzymes. The devices of this invention also comprise a coating (3) which surrounds the mixture (6) of one or more beneficial agents (4) and hydrogel

20 (5) or, in the two layer embodiments hereof, which surrounds both layers (6 and 7) except for the area in contact between such layers. The coating (3) comprises at least one water permeable polymer but, significantly and in contrast to many prior art devices, the coating need not be semi-permeable. Therefore, the coating (3) can be freely permeable to low molecular weight compounds. By way of example and not of limitation, such polymers for the coating (3) include cellulose acetate, ethyl-cellulose, silicone rubber,

25 cellulose nitrate, polyvinyl alcohols, cellulose acetate butyrate, cellulose succinate, cellulose laurate, cellulose palmitate and the like. For example, suitable coatings are obtained with cellulose acetate having an average molecular weight of 40K or 60K. Also suitable for the coating (3) of the devices of this invention are biodegradable polymers which do not degrade significantly (i.e., break or burst) during the delivery period. Examples of such biodegradable polymers include polylactic acid, polyglycolic acid and poly-

30 (lactide-coglycolide). A preferred polymer for the coating (3) is cellulose acetate.

The coating (3) can also comprise one or more porosigens such that, when the devices of this invention are placed in an environment of use, said porosigen(s) dissolve and effect the formation of a plurality of pores (2) in and through the coating (3).

As stated above, the porosigens can be employed alone or in combination to effect formation of the

35 pores (2) in and through the coating (3). The ratio of porosigen or porosigens to coating polymer can be varied as well as the choice of porosigens to be employed. Such variations are within the skill of those who practice in the art and will be determined by such factors as the solubility of the beneficial agent(s), the particle size of the agent(s), the molecular weight of the hydrogel and the desired rate of release. Examples of porosigens which will function to form the pores (2) in and through the coating (3) include inorganic salts

40 such as sodium chloride, potassium chloride, potassium phosphate and the like. Other effective porosigens are certain particulate organic compounds and salts thereof such as glucose, sucrose, lactose, succinic acid, sodium succinate, sodium carbonate and the like. Also effective porosigens are water-soluble polymers such as polyethyleneglycol (PEG), methyl cellulose, hydroxypropylmethyl cellulose, hydroxypropyl cellulose (HPC), polyethylene oxide (PEO) and the like.

45 Such pore-forming polymers must, however, have the ability to form a phase-separated coating when mixed with the coating forming polymer of this invention. That is to say, the porosigen polymer and the coating polymer cannot be totally miscible. Combinations of porosigens such as particulate organic compounds and salts thereof with inorganic salts and/or water-soluble polymers can be employed and are within the scope of this invention. Similarly, inorganic salts with water-soluble polymers can be employed as

50 porosigens in the devices of this invention. When the devices of this invention are to be used to deliver beneficial agents to an animal, the porosigen or porosigens employed must be pharmaceutically acceptable.

In addition to the formation of pores (2) upon placement of the devices of this invention into an environment of use through dissolution of one or more porosigens, the pores (2) can be preformed. Such

55 preformed pores can be produced by methods well known to those skilled in the art such as by gas generation in the coating (3) during formation of the coating (3); etched nuclear tracking; laser, sonic or mechanical drilling; or electric discharge. It is preferred, however, that such pores result from dissolution of porosigen(s) as described above.

In addition to the pores described above, or instead thereof, the coating can contain one or more holes. the holes may extend through only the coating on one face of the device or extend through the entire device. However, it is preferred that for the two layer embodiments of the devices of this invention of the type represented in Figure 3 wherein, in addition to the pores shown or instead thereof, one or more holes
 5 are contained in the coating, such holes do not extend through the entire device but only extend through the coating adjacent to the layer comprising beneficial agent. Such holes are made by standard methods known to those skilled in the art such as by mechanical, sonic or laser drilling.

In addition to the above-mentioned components of the devices of this invention, other common pharmaceutical excipients may be present. Examples of such excipients include, but are not limited to,
 10 binders such as microcrystalline cellulose, plasticizers such as polyethyleneglycol-600, and buffers such as sodium phosphate.

The devices of this invention can be prepared in a variety of sizes and shapes. The particular size and shape of the device will be determined, in part, by the particular use to which the device is to be put. For example, for oral administration of a drug, the device of this invention can be in the shape of a tablet or
 15 caplet, is of suitable size for containing the desired dosage of drug and is capable of oral administration. Other shapes of the devices of this invention include, by way of example and not of limitation, cylindrical or conical shapes suitable for administration of drugs intravaginally and/or rectally and convex shaped devices for ocular administration of drugs.

The devices of this invention can also be administered within a capsule comprising a water soluble wall.
 20 For example, the devices of this invention can be manufactured to be of suitable size for inclusion either singly or multiply within a gelatin capsule such that when the capsule dissolves the device or devices are released into the environment of use. While the devices to be included within a capsule can be of a variety of shapes, a preferred embodiment for such devices is spherical or substantially spherical. The exact number and size of such devices can and will be determined according to a variety of factors well known to
 25 those skilled in the art. For example, the environment of use, the beneficial agent or agents, the amount of beneficial agent and the rate of release are all factors to be considered in determining the size, shape and number of devices to be included in such capsules as well as the composition of the capsule.

While the actual process used to manufacture the devices of this invention may vary, one such preferred process is described below. Polymer to serve as the hydrogel (5) is blended according to
 30 standard methods well known to those skilled in the art in a predetermined ratio (e.g. weight percent) with one or more beneficial agents (4) and any excipients and/or osmotically effective solute(s). The ratio used will vary to a greater or lesser degree depending upon the particular hydrogel, the particular beneficial agent(s) used and the release rate to be achieved. Generally, however, the devices of this invention will comprise hydrogel in an amount from about 50 to about 95 weight percent based on the total weight of the
 35 mixture (6) of hydrogel (5) and beneficial agent(s) (4), and any excipients and/or osmotically effective solute(s). The hydrogel (5) can comprise more than one polymer in which case all polymers are blended with the beneficial agent(s) (4) and any excipients and/or osmotically effective solute(s) either sequentially or simultaneously. Optionally and preferably, the polymer(s) is sieved to a desired mesh cut prior to blending. If the desired device is to comprise one layer of the blended mixture (6) such as is shown in
 40 Figure 2, then the resulting blended mixture (6) is pressed into the desired shape such as a tablet or caplet using a conventional tableting press such as a Kilian LX-21 rotary tablet press (Kilian and Co., Koln, Germany).

Devices (1) of this invention which comprise two layers (6 and 7), such as those of the type shown in Figure 3, can be prepared in a similar but modified manner using a conventional bilayer tablet press. One
 45 layer consists of a mixture of one or more hydrogel polymers with one or more beneficial agents. The other layer consists of one or more hydrogel polymers, preferably of higher viscosity than, and generally of higher molecular weight than, the hydrogel polymer(s) which are mixed with the beneficial agent(s) in the first layer.

Spherical or substantially spherical embodiments such as depicted in Figures 4 and 5 can be prepared
 50 in a variety of ways known to those skilled in the art. In a preferred method, such embodiments are prepared using a Fuji extruder/spheronizer (Fuji Paudal Co., Tokyo, Japan) according to methods well known to those skilled in the art. When concentrically arranged embodiments are desired, hydrogel core beads are first prepared. These hydrogel beads then can be coated with a hydrogel/drug mixture using a Freund CF-granulator (CF-360; Freund Industrial Co., Tokyo, Japan) or a Glatt GPCG coating apparatus
 55 (Glatt Air Techniques, Ramsey, New Jersey).

Following formation of the desired shape in the press or extruder/spheronizer, coating (3) is applied to the entire surface of the mixture (6), or the surface of layers (6) and (7) which are not in contact with each other, or the outer surface of the outermost layer (6) of the concentric embodiment such as depicted in

Figure 5. The coating (3), which also can comprise porosigen(s), is applied to the mixture or outermost layer (6) or layers (6) and (7) according to standard methods well known to those skilled in the art. For those devices which are not spherical or substantially spherical, it is preferred that such coating be applied by spraying using, for example, a Freund Model HCT-30 Hicoater (Freund Industrial Co., Tokyo, Japan). For those devices which are spherical or substantially spherical, it is preferred that such coating be applied using, for example a Freund CF-granulator or a Glatt GPCG coating apparatus as described above. As an example, when cellulose acetate is employed for the coating, it can be sprayed as an acetone solution (5%) or as other solutions such as in acetone/methanol (9:1). Such cellulose acetate coatings from acetone/methanol solution result in a more opaque coating but have little or no observable impact on the functioning of the devices of this invention. The amount of coating (3) to be applied can be varied to affect the release rate of the devices but will generally be from about 5 to 50 weight percent of the total device weight with a range of from about 6 to 50 weight percent for those coatings (3) comprising porosigen(s).

For devices (1) of this invention which contain coating (3) in which the plurality of pores (2) is formed by means other than dissolution of porosigen(s), a preferred amount of coating (3) is in the range of from about 6 to 25 weight percent with an even more preferred range being from about 8 to 20 weight percent. If such coating (3) contains porosigen(s), then a preferred amount of coating (3) for the devices (1) of this invention is a range of from about 8 to 30 weight percent with an even more preferred range being from about 10 to 25 weight percent.

If the coating (3) contains one or more porosigens, then the pores (2) will be formed *in situ* when the device (1) is placed in the environment of use. Of course, while not necessarily advantageous, the pores (2) of such devices can be preformed by placing the device first into a suitable aqueous environment then, upon dissolution or partial dissolution of the porosigen(s), into the environment of use.

If the coating (3) does not contain any porosigen, then the pores (2) can be formed by other methods well known to those skilled in the art. For example, pores (2) in coating (3) can be formed by gas generation during formation of the coating (3) following application of the coating mixture to the device. Other processes to produce pores (2) in coating (3) include the use of etched nuclear tracking, the use of laser, sonic or mechanical drilling and the use of electrical discharge. Additionally, in coatings without porosigens, pores can be formed in the environment of use by bursting of weak portions of the membrane as a result of the internal pressure generated by the swelling hydrogel.

A combination of the above described methods for producing pores (2) in coating (3) can be employed and are within the skill of those skilled in the art enabled by the disclosure herein. Such devices are within the scope of this invention.

When employing porosigens to form the pores (2) in coating (3), particular attention is to be paid to the beneficial agent or agents to be delivered by the device (1). If the beneficial agent is soluble, then pore size is not as crucial as when the agent is insoluble. Indeed, the devices of this invention will function to controllably release certain agents even though the pore size is less than 0.1 micron where such agent is soluble. However, where delivery of an insoluble agent, such as the drug glipizide, is desired, then the porosigen employed must be such that, upon dissolution, pores (2) having diameters greater than the particle size of the agent are formed in and through the coating (3). For example, sucrose of a selected mesh cut can be employed in a suspension comprising cellulose acetate to form a coating (3) which, upon subsequent dissolution of the sucrose will yield pores (2) of a preselected (i.e., mesh cut) size. Similarly, commercially available sucrose beads can be so employed. For certain beneficial agents and/or environments of use, it may be advantageous or preferable to include more than one porosigen. For example, coating mixtures which comprise coating polymer, water soluble polymer and sucrose such as cellulose acetate/polyethylene glycol-600 (1:1) with 50% particulate sucrose can be suitably employed. The choice of porosigen or porosigens as well as the amount thereof employed in the coating mixture can be readily determined by those skilled in the art enabled by this disclosure.

Similarly, when the pores (2) in coating (3) are formed by means other than by dissolution of porosigen(s), the nature of the beneficial agent(s) to be delivered by the device (1) must be considered to insure that the pores (2) are of varying diameter according to the methods described above are well known to those skilled in the art.

When the devices of this invention are to contain one or more holes in the coating (3) or through the device (1), then, after such devices have been coated as described above, the desired number and size holes are drilled through the coating or device according to standard methods such as mechanical, sonic or laser drilling.

Methods for using the devices of this invention include administration of the appropriate devices to animals via oral administration or by insertion of the appropriate devices into a body cavity of the animal. Devices of this invention can also be used to deliver agents to such environments of use as fish tanks, soil

and aqueous chemical and/or enzymatic reaction systems. In such cases, the devices are placed into the desired environment of use. The devices of this invention require that any such environment of use be either aqueous or provide for contact of the device with water or other aqueous medium.

The following examples will serve to illustrate the devices of this invention and are not to be construed as limiting the scope hereof to those embodiments specifically exemplified.

EXAMPLE 1

Doxazosin mesylate was blended with 20K molecular weight polyethylene oxide (PEO-20K) in a ratio of 2:98 and the blended mixture was pressed into 500 mg tablets in a Carver press using 13/32 inch standard concave punches under 2 metric tons for 2 seconds. The tablets were then spray coated with a 9:1 acetone/methanol solution of cellulose acetate (2.2%) and hydroxypropylcellulose (HPC) (2.2%). The weight ratio of cellulose acetate to HPC in the coating was 1:1, and the final coating was 12 weight percent of the total device weight.

EXAMPLE 2

The procedure of Example 1 was followed up to the coating of the tablets where the coating mixture was applied to an amount equal to 18.6 weight percent of the total device weight.

EXAMPLE 3

The procedure of Example 1 was followed up to the coating of the tablets where the coating mixture was applied to an amount equal to 23.8 weight percent of the total device weight.

EXAMPLE 4

Tablets of 500 mg were prepared as follows. Polyethylene oxide (14K molecular weight) (PEO-14K) was blended with doxazosin mesylate at a ratio of 9:1 and pressed into 500 mg tablets as described in Example 1. Then, the tablets were spray coated with a 9:1 acetone/methanol solution of cellulose acetate (2.2%) and HPC (2.2%). The weight ratio of cellulose acetate to HPC in the coat was 1:1, and the final coating was 13.1 weight percent of the total device weight.

EXAMPLE 5

The procedure of Example 4 was followed to form tablets which were then spray coated with an 8:2 acetone/methanol solution of cellulose acetate (2.9%) and HPC (4.3%). The weight ratio of cellulose acetate to HPC in the coating was 2:3, and the final coating was 14 weight percent of the total device weight.

EXAMPLE 6

The procedure of Example 4 was followed to form tablets which were then spray coated with an 8:2 acetone/methanol solution of cellulose acetate (1.5%) and HPC (3.5%). The weight ratio of cellulose acetate to HPC in the coating was 3:7, and the final coating was 13.1 weight percent of the total device weight.

EXAMPLE 7

A blend of PEO of 8K molecular weight (PEO-8K) and doxazosin mesylate (98:2) was prepared and pressed into 500 mg tablets in a Carver press using 13/32 inch standard concave punches under 2 metric tons for 2 seconds. The tablets were then spray coated with a 9:1 acetone/methanol solution of cellulose acetate (3%) and PEO-8K (3%). The weight ratio of cellulose acetate to PEO-8K in the coating was 1:1, and the final coating was 12.7 weight percent of the total device weight.

EXAMPLE 8

A blend of polyethylene oxide (8K molecular weight) (PEO-8K) and doxazosin mesylate (9:1) was prepared and pressed into 500 mg tablets in a Carver press using 13/32 inch standard concave punches under 2 metric tons for 2 seconds. The tablets were spray coated with a 9:1 acetone/methanol solution of

cellulose acetate (3.5%) and polyethylene glycol (molecular weight 600) (PEG-600) (1.5%). The weight ratio of cellulose acetate to PEG-600 in the coating was 7:3, and the final coating was 12.5 weight percent of the total device weight.

5 **EXAMPLE 9**

The procedure of Example 8 was followed to produce tablets which were then spray coated with a 9:1 acetone/methanol solution of cellulose acetate (3.0%) and PEG-600 (2.0%). The weight ratio of cellulose acetate to PEG-600 in the coating was 3:2, and the final coating was 12.9 weight percent of the total device weight.

EXAMPLE 10

The procedure of Example 8 was followed to produce tablets which were then spray coated with a 9:1 acetone/methanol solution of cellulose acetate (2.5%) and PEG-600 (2.5%). The weight ratio of cellulose acetate to PEG-600 in the coating was 1:1, and the final coating was 13.5 weight percent of the total device weight.

EXAMPLE 11

A blend of 100K molecular weight polyethylene oxide (PEO-100K) and the insoluble drug glipizide (95:5) was prepared and pressed into 500 mg tablets using a Manesty Type-F3 tablet press (Manesty Machines Ltd., Liverpool, England). The tablets were spray-coated with a suspension of sucrose (50/60 mesh) in an acetone solution of cellulose acetate (2.5%) and PEG-600 (2.5%). The weight ratio of cellulose acetate to PEG-600 to sucrose in the coating was 1:1:2. The final coating was 13.7 weight percent of the total device weight.

EXAMPLE 12

The procedure of Example 11 was followed to produce tablets as described therein which were then spray coated with suspension of sucrose (30/40 mesh) in an acetone solution of cellulose acetate (4%) and PEG-600 (1%). The weight ratio of cellulose acetate to PEG-600 to sucrose in the coating was 4:1:5. The final coating was 11.8 weight percent of the total device weight.

35 **EXAMPLE 13**

The release rates for the devices described in Examples 1-12 were determined according to the procedures described below.

For those devices which contained doxazosin, the device under study was placed in an individual well of a USP dissolution apparatus which well contained 1000 ml of water as the release medium. The well containing the device was stirred at 100 rpm and aliquots of the release medium were removed over time. The aliquots were assayed for doxazosin by measuring UV absorbance at 246 nm.

For those devices which contained glipizide, the device under study was placed in an individual well of a USP dissolution apparatus which well contained 1000 ml of USP Simulated Intestinal Fluid (SIF) without enzymes as the release medium. The well containing the device was stirred at 100 rpm and aliquots of the release medium were removed over time. The aliquots were assayed for glipizide by measuring UV absorbance at 275 nm.

Employing the above described assay procedures, the devices of Examples 1-12 were assayed for release of the beneficial agent and the data is shown in the Tables described below.

50

55

TABLE I

Time(hrs.)	Percent of Doxazosin Released over Time from Devices of Examples 1, 2 and 3		
	Percent Doxazosin Released		
	Device of Example 1	Device of Example 2	Device of Example 3
0	0	0	0
1.50	0	0	0
3.17	12.6	1.3	0
4.0	18.4	5.3	0
5.0	25.8	8.9	1.2
5.67	30.7	11.5	2.4
7.67	37.6	18.5	5.0
9.83	52.2	26.9	8.8
11.0	54.6	29.9	10.9
12.25	60.0	35.2	13.2
13.10	61.6	37.6	14.2
22.0	76.5	57.5	29.1
24.0	83.2	61.1	31.8
26.0	85.7	63.6	33.0

Table I, above, shows the release of doxazosin as percent released over time of the devices of Examples 1, 2 and 3. The data show that the rate of release can be varied as a function of the amount of coating (3) applied to the device. For the devices of Examples 1, 2 and 3, as the amount of coating increased the rate of release decreased.

TABLE II

Time(hrs.)	Percent of Doxazosin Released over Time from Devices of Examples 4, 5 and 6		
	Percent of Doxazosin Released		
	Device of Example 4	Device of Example 5	Device of Example 6
0	0	0	0
1.25	0	-	-
1.33	-	7.0	23.8
2.0	-	15.9	35.9
2.16	3.5	-	-
3.0	-	30.2	53.0
3.1	9.3	-	-
4.0	-	43.8	68.3
4.1	15.4	-	-
5.0	-	54.3	80.4
5.16	22.4	-	-
6.0	-	61.5	88.1
6.1	28.8	-	-
7.0	-	67.8	92.7
7.1	34.5	-	-
7.85	38.7	-	-
8.0	-	74.0	96.6
10.33	52.4	-	-
11.5	57.1	-	-

Table II, above, shows the release of doxazosin as percent released over time from the devices of Examples 4, 5 and 6. The data show that the rate of release can be varied as a function of the amount of porosity and, hence, pores (2) contained in the coating (3). For the devices of Examples 4, 5 and 6, the

rate of release increased as the amount of porosigen (i.e., hydroxypropyl cellulose) in the coating was increased.

Table III, below, presents data showing the release rate of doxazosin as percent released over time for the device of Example 7.

TABLE III

Percent of Doxazosin Released over Time from the Device of Example 7	
Time(hrs.)	Percent Doxazosin Released
0	0
0.5	2.7
1.0	13.4
1.5	21.0
2.0	28.9
2.5	36.4
3.0	44.2
3.5	51.5
4.0	57.3
4.5	61.8
5.0	66.1
5.75	70.6
7.17	76.5
23.33	90.8

TABLE IV

Percent of Doxazosin Released over Time from Devices of Examples 8, 9 and 10			
Time(hrs.)	Percent Doxazosin Released		
	Device of Example 8	Device of Example 9	Device of Example 10
0	0	0	0
0.5	0	0	0
1.0	0	0	10.0
1.5	0	0	22.4
2.0	0	10.9	33.0
2.5	0	20.4	43.4
3.0	1.5	29.1	49.4
3.5	3.9	36.3	54.3
4.0	7.8	41.5	59.5
4.5	11.2	45.4	62.6
5.0	15.2	49.2	65.7
5.75	20.6	52.6	67.6
7.17	27.6	58.6	72.0
23.33	61.1	78.0	85.2

Table IV, above, shows the release of doxazosin as percent released over time from the devices of Examples 8, 9 and 10. The rate of release of doxazosin increased as the amount of PEG-600 in the coating increased. Examination of the devices of Examples 8, 9 and 10 by scanning electron microscopy after release of doxazosin resulted in the inability to locate any pores in the coating at a 0.1 micron lower limit of detection. Therefore, the doxazosin which had a particle size greater than 0.1 micron exited from these devices in solution. Nonetheless, the devices were capable of releasing doxazosin in a controlled manner over time and, further, the rate of release can be controlled by the amount of PEG 600 in the coating. Of course, the limitation for such devices of Examples 8, 9 and 10 is that the beneficial agent(s) must be either soluble in water or, perhaps, of a very small (less than 0.1 micron) particle size.

TABLE V

Percent of Glipizide Released over Time from Devices of Examples 11 and 12		
Time(hrs.)	Percent Glipizide Released	
	Device of Example 11	Device of Example 12
0	0	0
1.0	12.7	0.7
2.0	26.1	5.8
3.33	40.0	14.9
5.0	50.3	25.6
6.0	56.6	32.9
8.25	63.8	41.1
9.67	67.4	45.2
21.5	76.6	58.8

Table V, above, shows the release of glipizide, an insoluble drug, as percent released over time from the devices of Examples 11 and 12. Examination of the devices of Examples 11 and 12 by scanning electron microscopy following release of glipizide revealed the presence in the coating of pores larger than 245 microns which had been formed upon dissolution of the particulate sucrose.

EXAMPLE 14

Tablets (500 mg) were prepared from a powder blend consisting of PEO-100K, sodium chloride, and glipizide in the weight ratio 76:20:4, using a Carver press under 2 metric tons for 2 seconds. These tablets were spray-coated with a suspension of sucrose (60/80 mesh) in an acetone solution of cellulose acetate (2.5 wt%) and PEG-600 (2.5 wt%). The final weight ratio of cellulose acetate to PEG-600 to sucrose was 1:1:2. The final coating level was 16 weight percent of the final coated tablet weight. The *in vitro* release of glipizide from these tablets into 0.004 M Tris, pH 8.7, was carried out as described in Example 13 and glipizide was assayed by HPLC using a 3.9 mm x 15 cm Novapack C₁₈ column (Waters Associates, Milford, Massachusetts) with a mobile phase consisting of 50 volume percent 0.05M sodium phosphate (pH 7.5) and 50 volume percent methanol. The flow rate was 1.0 ml/min. and detection of glipizide was at 227 nm. The *in vitro* release kinetic profile, shown in Table VI, below, demonstrates controlled release of glipizide from these tablets.

TABLE VI

Percent of Glipizide Released over Time from the Device of Example 14		
	Time(hrs.)	Percent Glipizide Released
	0	0
	0.5	15.4
	1.0	30.4
	1.5	44.8
5	2.0	55.5
	3.0	69.9
10	4.0	77.3
	5.0	81.9
	6.0	84.6
15	7.0	86.6
	8.0	87.0
	9.0	88.7
	10.0	89.3
20	11.0	89.7
	13.0	91.0
	15.0	91.6

25 Claims

1. A dispensing device for dispensing to an environment a beneficial agent, the device comprising a coating (3) through which the agent has passage when the device is disposed in and exposed to said environment and a core comprising a mixture (6) which comprises from 50 to 98 weight percent of a hydrogel (5) based on the total weight of the mixture and a charge of said agent (4), the hydrogel being a water swellable polymer or a combination of two or more such polymers.
2. A dispensing device as claimed in claim 1 and which comprises:
 - (a) a core which comprises a mixture (6) comprising one or more beneficial agents (4) and hydrogel (5); and
 - (b) a coating (3) containing a plurality of pores (2) which coating surrounds the mixture.
3. A dispensing device as claimed in claim 2 and which comprises:
 - (a) a first layer (6) comprising a mixture of one or more beneficial agents (4) and hydrogel (5);
 - (b) a second layer (7) disposed in overlying or underlying adjacent containing relation to said first layer (6) and comprising hydrogel (8); and
 - (c) a coating (3) containing a plurality of pores (2) which coating surrounds the combination of said first and second layers (6,7).
4. A dispensing device as claimed in Claim 2 and which comprises:-
 - (a) an innermost layer (7) comprising hydrogel (8);
 - (b) an outermost layer (6) adjacent to and surrounding the innermost layer (7) and comprising a mixture of one or more beneficial agents (4) and hydrogel (5); and
 - (c) a coating (3) containing a plurality of pores (2) which coating surrounds the outermost layer (6).
5. A dispensing device as claimed in Claim 1 and which comprises:-
 - (a) a core which comprises a mixture (6) comprising one or more beneficial agents (4) and hydrogel (5); and
 - (b) a coating (3) containing at least one hole which coating surrounds the mixture.
6. A dispensing device as claimed in Claim 5 and which comprises:-
 - (a) a first layer (6) comprising a mixture of one or more beneficial agents (4) and hydrogel (5);

(b) a second layer (7) disposed in overlying or underlying adjacent contacting relation to said first layer (6) and comprising hydrogel (8); and
(c) a coating (3) containing at least one hole adjacent to the first layer (6) which coating (3) surrounds the combination of said first and second layers (6,7).

7. A dispensing device as claimed in Claim 5 and which comprises:
(a) an innermost layer (7) comprising hydrogel (8);
(b) an outermost layer (6) adjacent to and surrounding the innermost layer (7) and comprising a mixture of one or more beneficial agents (4) and hydrogel (5); and
(c) a coating (3) containing at least one hole which coating surrounds the outermost layer (6).

8. A dispensing device as claimed in any one of Claims 2 to 7 wherein the coating (3) contains a plurality of pores (2) and at least one hole in communication with the mixture (6) comprising hydrogel (5) and agent (4).

9. A dispensing device as claimed in any one of Claims 5 to 7 wherein the coating (3) comprises a polymer and one or more porosigens.

10. A dispensing device as claimed in Claim 1 and which comprises:-
(a) a core which comprises a mixture (6) comprising one or more beneficial agents (4) and hydrogel (5); and
(b) a coating (3) which surrounds the mixture (6) and which comprises a polymer and one or more porosigens.

11. A dispensing device as claimed in Claim 10 and which comprises:-
(a) a first layer (6) comprising a mixture of one or more beneficial agents (4) and hydrogel (5);
(b) a second layer (7) disposed in overlying or underlying adjacent contacting relation to said first layer (6) and comprising hydrogel (8); and
(c) a coating (3) which comprises a polymer and one or more porosigens and which coating surrounds the combination of said first and second layers (6,7).

12. A dispensing device as claimed in Claim 10 and which comprises:
(a) an innermost layer (7) comprising hydrogel (5);
(b) an outermost layer (6) adjacent to and surrounding the innermost layer (7) and comprising a mixture of one or more beneficial agents (4) and hydrogel; and
(c) a coating (3) which surrounds the outermost layer (6) and which comprises a polymer and one or more porosigens.

13. A dispensing device as claimed in any one of Claims 9 to 12 wherein the porosigen is one or more water-soluble polymers, one or more water-soluble polymers and one or more inorganic salts, one or more water-soluble polymers and one or more water-soluble particulate organic compounds or salts thereof, or one or more inorganic salts and one or more water-soluble particulate organic compounds or salts thereof.

14. A dispensing device as claimed in Claim 13 wherein the water-soluble polymer is hydroxypropyl cellulose, polyethylene glycol, polyethylene oxide or a mixture of two or more thereof.

15. A dispensing device as claimed in Claim 13 wherein the water-soluble polymer is polyethylene glycol-600 and the water-soluble particulate organic compound is sucrose.

16. A dispensing device as claimed in any preceding claim wherein the mixture (6) additionally comprises an osmotically effective solute.

17. A dispensing device as claimed in any preceding claim wherein the core comprises either an innermost layer (7) comprising hydrogel (5) and an outermost layer (6) adjacent to and surrounding the innermost layer (7) and comprising a mixture of one or more beneficial agents (4) and hydrogel (5) or a first layer (6) comprising a mixture of one or more beneficial agents (4) and hydrogel (5) and a second layer (7) disposed in overlying or underlying adjacent contacting relation to said first layer (6) and comprising

hydrogel (8); and wherein one or both such layers (6,7) include an osmotically effective solute.

18. A dispensing device as claimed in any preceding claim wherein the beneficial agent (4) is a drug; the hydrogel (5) is polyethylene oxide; and the coating (3) comprises cellulose acetate.

19. A capsule which comprises a water-soluble wall encapsulating one or more dispensing devices as claimed in any preceding claim.

20. A method for the controlled delivery of one or more beneficial agents to an environment of use other than for diagnostic or therapeutic purposes practiced on a human or non-human animal body which method comprises placing into said environment a dispensing device as claimed in any one of Claims 1 to 18 or a capsule as claimed in Claim 19.

Patentansprüche

1. Spendervorrichtung zur Abgabe eines für die Umgebung vorteilhaften bzw. nützlichen Mittels, wobei die Vorrichtung eine Beschichtung (3), durch die das Mittel hindurchtritt, wenn die Vorrichtung in einer Umgebung angeordnet ist und dieser ausgesetzt ist, und einen Kern umfaßt, der eine Mischung (6) umfaßt, die 50 bis 98 Gew.-% eines Hydrogels (5), bezogen auf das Gesamtgewicht der Mischung, und eine Beladung mit diesem Mittel (4) umfaßt, wobei das Hydrogel ein in Wasser quellbares Polymer oder eine Kombination von zwei oder mehr solcher Polymere ist.

2. Spendervorrichtung nach Anspruch 1 umfassend:

- (a) einen Kern, der eine Mischung (6) umfaßt, die ein oder mehrere nützliche Mittel (4) und ein Hydrogel (5) umfaßt und
- (b) eine Beschichtung (3), die eine Vielzahl von Poren (2) enthält, wobei diese Beschichtung die Mischung umgibt.

3. Spendervorrichtung nach Anspruch 2 umfassend:

- (a) eine erste Schicht (6), die eine Mischung aus ein oder mehreren nützlichen Mitteln (4) und einem Hydrogel (5) umfaßt;
- (b) eine zweite Schicht (7), die in benachbartem Kontakt zu der ersten Schicht (6) darüberliegend oder darunterliegend angeordnet ist und das Hydrogel (8) umfaßt und
- (c) eine Beschichtung (3), die eine Vielzahl von Poren (2) enthält, wobei die Beschichtung die Kombination aus erster und zweiter Schicht (6, 7) umgibt.

4. Spendervorrichtung nach Anspruch 2 umfassend:

- (a) eine innerste Schicht (7), die ein Hydrogel (8) umfaßt;
- (b) eine äußerste Schicht (6), die der innersten Schicht (7) benachbart ist und diese umgibt und eine Mischung aus einem oder mehreren nützlichen Mitteln (4) und ein Hydrogel (5) umfaßt und
- (c) eine Beschichtung (3), die eine Vielzahl von Poren (2) enthält, wobei die Beschichtung die äußerste Schicht (6) umgibt.

5. Spendervorrichtung nach Anspruch 1 umfassend:

- (a) einen Kern, der eine Mischung (6) umfaßt, die ein oder mehrere nützliche Mittel (4) und ein Hydrogel (5) umfaßt und
- (b) eine Beschichtung (3), die mindestens ein Loch enthält, wobei die Beschichtung die Mischung umgibt.

6. Spendervorrichtung nach Anspruch 5 umfassend:

- (a) eine erste Schicht (6), die eine Mischung aus einem oder mehreren nützlichen Mitteln (4) und ein Hydrogel (5) umfaßt;
- (b) eine zweite Schicht (7), die in benachbartem Kontakt zu der ersten Schicht (6) darüberliegend oder darunterliegend angeordnet ist und ein Hydrogel (8) umfaßt und
- (c) eine Beschichtung (3), die mindestens ein Loch benachbart zu der ersten Schicht (6) enthält, wobei die Beschichtung (3) die Kombination aus erster und zweiter Schicht (6, 7) umgibt.

7. Spendervorrichtung nach Anspruch 5 umfassend:

- (a) eine innerste Schicht (7), die ein Hydrogel (8) umfaßt;
 (b) eine äußerste Schicht (6), die der innersten Schicht (7) benachbart ist und diese umgibt und eine Mischung aus einem oder mehreren nützlichen Mitteln (4) und einem Hydrogel (5) umfaßt und
 (c) eine Beschichtung (3), die mindestens ein Loch enthält, wobei die Beschichtung die äußerste Schicht (6) umgibt.
- 5
8. Spendervorrichtung nach einem der Ansprüche 2 bis 7, worin die Beschichtung (3) eine Vielzahl von Poren (2) und mindestens ein Loch enthält, das mit der Mischung (6), die das Hydrogel (5) und das Mittel (4) umfaßt, in Verbindung steht.
- 10
9. Spendervorrichtung nach einem der Ansprüche 5 bis 7, worin die Beschichtung (3) ein Polymer und ein oder mehrere Porosigene umfaßt.
10. Spendervorrichtung nach Anspruch 1 umfassend:
- 15 (a) einen Kern, der eine Mischung (6) umfaßt, die ein oder mehrere nützliche Mittel (4) und ein Hydrogel (5) umfaßt und
 (b) eine Beschichtung (3), die die Mischung (6) umgibt und ein Polymer und ein oder mehrere Porosigene umfaßt.
- 20 11. Spendervorrichtung nach Anspruch 10 umfassend:
 (a) eine erste Schicht (6), die eine Mischung aus einem oder mehreren nützlichen Mitteln (4) und ein Hydrogel (5) umfaßt;
 (b) eine zweite Schicht (7), die in benachbartem Kontakt zu der ersten Schicht (6) darüberliegend oder darunterliegend angeordnet ist und ein Hydrogel (8) umfaßt und
 25 (c) eine Beschichtung (3), die ein Polymer und ein oder mehrere Porosigene umfaßt, wobei die Beschichtung die Kombination aus erster und zweiter Schicht (6, 7) umgibt.
12. Spendervorrichtung nach Anspruch 10 umfassend:
 (a) eine innerste Schicht (7), die ein Hydrogel (5) umfaßt;
 30 (b) eine äußerste Schicht (6), die zu der innersten Schicht (7) benachbart ist und diese umgibt und eine Mischung aus einem oder mehreren nützlichen Mitteln (4) und einem Hydrogel umfaßt und
 (c) eine Beschichtung (3), die die äußerste Schicht (6) umgibt und ein Polymer und ein oder mehrere Porosigene umfaßt.
- 35 13. Spendervorrichtung nach einem der Ansprüche 9 bis 12, worin das Porosigen aus einem oder mehreren wasserlöslichen Polymeren, einem oder mehreren wasserlöslichen Polymeren und einem oder mehreren anorganischen Salzen, einem oder mehreren wasserlöslichen Polymeren und einer oder mehreren wasserlöslichen teilchenförmigen organischen Verbindungen oder Salzen davon, oder einem oder mehreren anorganischen Salzen und einer oder mehreren wasserlöslichen teilchenförmigen organischen Verbindungen oder Salzen davon besteht.
- 40
14. Spendervorrichtung nach Anspruch 13, worin das wasserlösliche Polymer Hydroxypropylcellulose, Polyethylenglykol, Polyethylenoxid oder eine Mischung von zwei oder mehreren davon ist.
- 45 15. Spendervorrichtung nach Anspruch 13, worin das wasserlösliche Polymer Polyethylenglykol 600 ist und die wasserlösliche teilchenförmige organische Verbindung Saccharose ist.
16. Spendervorrichtung nach einem der vorhergehenden Ansprüche, worin die Mischung (6) zusätzlich einen osmotisch wirksamen gelösten Stoff umfaßt.
- 50
17. Spendervorrichtung nach einem der vorhergehenden Ansprüche, worin der Kern entweder eine innerste Schicht (7), die das Hydrogel (5) umfaßt, und eine äußerste Schicht (6), die der innersten Schicht (7) benachbart ist und diese umgibt und eine Mischung aus einem oder mehreren nützlichen Mitteln (4) und ein Hydrogel (5) umfaßt, oder eine erste Schicht (6), die eine Mischung aus einem oder mehreren nützlichen Mitteln (4) und einem Hydrogel (5) umfaßt und eine zweite Schicht (7), die in benachbartem Kontakt zu der ersten Schicht (6) darüberliegend oder darunterliegend angeordnet ist und ein Hydrogel (8) umfaßt, umfaßt; und worin eine oder beide Schichten (6, 7) einen osmotisch wirksamen gelösten Stoff enthalten.
- 55

18. Spendervorrichtung nach einem der vorhergehenden Ansprüche, worin das nützliche Mittel (4) ein Arzneimittel ist; das Hydrogel (5) Polyethylenoxid ist und die Beschichtung (3) Celluloseacetat enthält.

5 19. Kapseln umfassend eine wasserlösliche Wand, die ein oder mehrere Spendervorrichtungen nach einem der vorhergehenden Ansprüche einkapselt.

20. Verfahren zur kontrollierten Abgabe eines oder mehrerer nützlicher Mittel an eine Umgebung für andere als diagnostische oder therapeutische Zwecke, die an einem menschlichen oder nicht menschlichen tierischen Körper angewendet werden, wobei das Verfahren umfaßt, daß man in der Umgebung eine
10 Spendervorrichtung nach einem der Ansprüche 1 bis 18 oder eine Kapsel nach Anspruch 19 anordnet.

Revendications

15 1. Dispositif de distribution pour délivrer à un environnement un agent à effet bénéfique, le dispositif comprenant un revêtement (3) à travers lequel l'agent peut passer lorsque le dispositif est placé dans, et mis en contact avec, ledit environnement et un noyau constitué d'un mélange (6) qui comprend 50 à 98 % en poids d'un hydrogel (5) sur la base du poids total du mélange et une charge dudit agent (4), l'hydrogel étant un polymère pouvant gonfler dans l'eau ou une association de deux ou plus de deux de tels polymères.

20 2. Dispositif de distribution suivant la revendication 1, qui comprend :
(a) un noyau qui est constitué d'un mélange (6) comprenant un ou plusieurs agents à effet bénéfique (4) et un hydrogel (5) ; et
(b) un revêtement (3) contenant une pluralité de pores (2), revêtement qui entoure le mélange.

25 3. Dispositif de distribution suivant la revendication 2, qui comprend :
(a) une première couche (6) comprenant un mélange d'un ou plusieurs agents à effet bénéfique (4) et d'un hydrogel (5) ;
(b) une seconde couche (7) en position adjacente par contact avec ladite première couche (6), au-dessus ou au-dessous de celle-ci, et comprenant un hydrogel (8) ; et
30 (c) un revêtement (3) contenant une pluralité de pores (2), revêtement qui entoure l'association desdites première et seconde couches (6, 7).

35 4. Dispositif de distribution suivant la revendication 2, qui comprend :
(a) une couche intérieure (7) comprenant un hydrogel (8) ;
(b) une couche extérieure (6) adjacente à, et entourant, la couche intérieure (7) et comprenant un mélange d'un ou plusieurs agents à effet bénéfique (4) et d'un hydrogel (5) ; et
(c) un revêtement (3) contenant une pluralité de pores (2), revêtement qui entoure la couche
40 extérieure (6).

5. Dispositif de distribution suivant la revendication 1, qui comprend :
(a) un noyau qui comprend un mélange (6) comprenant un ou plusieurs agents à effet bénéfique (4) et un hydrogel (5) ; et
(b) un revêtement (3) contenant au moins un trou, revêtement qui entoure le mélange.

45 6. Dispositif de distribution suivant la revendication 5, qui comprend :
(a) une première couche (6) comprenant un mélange d'un ou plusieurs agents à effet bénéfique (4) et d'un hydrogel (5) ;
(b) une seconde couche (7) en position adjacente par contact avec ladite première couche (6), au-dessus ou au-dessous de celle-ci, et comprenant un hydrogel (8) ; et
50 (c) un revêtement (3) contenant au moins un trou, adjacent à la première couche (6), revêtement (3) qui entoure l'association desdites première et seconde couches (6, 7).

7. Dispositif de distribution suivant la revendication 5, qui comprend :
55 (a) une couche intérieure (7) comprenant un hydrogel (8) ;
(b) une couche extérieure (6) adjacente à, et entourant, la couche intérieure (7) et comprenant un mélange d'un ou plusieurs agents à effet bénéfique (4) et d'un hydrogel (5) ; et
(c) un revêtement (3) contenant au moins un trou, revêtement qui entoure la couche extérieure (6).

8. Dispositif de distribution suivant l'une quelconque des revendications 2 à 7, dans lequel le revêtement (3) contient une pluralité de pores (2) et au moins un trou en communication avec le mélange (6) comprenant l'hydrogel (5) et l'agent (4).
- 5 9. Dispositif de distribution suivant l'une quelconque des revendications 5 à 7, dans lequel le revêtement (3) comprend un polymère et un ou plusieurs agents engendrant des pores.
10. Dispositif de distribution suivant la revendication 1, qui comprend :
 - (a) un noyau qui comprend un mélange (6) renfermant un ou plusieurs agents à effet bénéfique (4) et un hydrogel (5) ; et
 - 10 (b) un revêtement (3) qui entoure le mélange (6) et qui comprend un polymère et un ou plusieurs agents engendrant des pores.
11. Dispositif de distribution suivant la revendication 10, qui comprend :
 - 15 (a) une première couche (6) comprenant un mélange d'un ou plusieurs agents à effet bénéfique (4) et d'un hydrogel (5) ;
 - (b) une seconde couche (7) en position adjacente par contact avec ladite première couche (6), au-dessus ou au-dessous de celle-ci, et comprenant un hydrogel (8) ; et
 - (c) un revêtement (3) qui comprend un polymère et un ou plusieurs agents engendrant des pores,
 - 20 revêtement qui entoure l'association desdites première et seconde couches (6, 7).
12. Dispositif de distribution suivant la revendication 10, qui comprend :
 - (a) une couche intérieure (7) comprenant un hydrogel (5) ;
 - (b) une couche extérieure (6) adjacente à, et entourant, la couche intérieure (7) et comprenant un
 - 25 mélange d'un ou plusieurs agents à effet bénéfique (4) et d'un hydrogel ; et
 - (c) un revêtement (3) qui entoure la couche la plus extérieure (6) et qui comprend un polymère et un ou plusieurs agents engendrant des pores.
13. Dispositif de distribution suivant l'une quelconque des revendications 9 à 12, dans lequel l'agent engendrant des pores consiste en un ou plusieurs polymères hydrosolubles, un ou plusieurs polymères hydrosolubles et un ou plusieurs sels inorganiques, un ou plusieurs polymères hydrosolubles et un ou plusieurs composés organiques hydrosolubles en particules ou leurs sels, ou bien un ou plusieurs sels inorganiques et un ou plusieurs composés organiques hydrosolubles en particules ou leurs sels.
- 30 14. Dispositif de distribution suivant la revendication 13, dans lequel le polymère hydrosoluble est l'hydroxypropylcellulose, le polyéthylène-glycol, un polymère d'oxyde d'éthylène ou un mélange de deux ou plus de deux d'entre eux.
- 35 15. Dispositif de distribution suivant la revendication 13, dans lequel le polymère hydrosoluble est le polyéthylène-glycol 600 et le composé organique hydrosoluble en particules est le saccharose.
- 40 16. Dispositif de distribution suivant l'une quelconque des revendications précédentes, dans lequel le mélange (6) comprend en outre un soluté à effet osmotique.
- 45 17. Dispositif de distribution suivant l'une quelconque des revendications précédentes, dans lequel le noyau comprend une couche intérieure (7) renfermant un hydrogel (5) et une couche extérieure (6) adjacente à, et entourant, la couche intérieure (7) et comprenant un mélange d'un ou plusieurs agents à effet bénéfique (4) et d'un hydrogel (5), ou bien une première couche (6) comprenant un mélange d'un ou plusieurs agents à effet bénéfique (4) et d'un hydrogel (5) et une seconde couche (7) en
- 50 position adjacente par contact avec ladite première couche (6), au-dessus ou au-dessous de celle-ci, et comprenant un hydrogel (8) ; et dans lequel une des, ou les deux, couches (6, 7) comprennent un soluté à effet osmotique.
- 55 18. Dispositif de distribution suivant l'une quelconque des revendications précédentes, dans lequel l'agent à effet bénéfique (4) est un médicament ; l'hydrogel (5) est un polymère d'oxyde d'éthylène ; et le revêtement (3) comprend de l'acétate de cellulose.

19. Capsule qui comprend une paroi hydrosoluble entourant un ou plusieurs dispositifs de distribution suivant l'une quelconque des revendications précédentes.

5 **20.** Procédé pour la libération contrôlée d'un ou plusieurs agents à effet bénéfique dans un environnement d'utilisation, autre qu'à des fins de diagnostic ou de thérapeutique sur l'organisme de l'homme ou d'un animal autre que l'homme, procédé qui comprend la mise en place dans ledit environnement d'un dispositif de distribution suivant l'une quelconque des revendications 1 à 18 ou d'une capsule suivant la revendication 19.

10

15

20

25

30

35

40

45

50

55

Figure 1




Figure 2




Figure 3




Figure 4




Figure 5




Figure 6

